



EN 13707



## TECHNICAL DATA SHEET

SYSTEMS		PRODUCT NAME			CARRIER TYPE
EN 13707 - Top layer in multilayer system without permanent surface protection (02.T) -		<b>GOLD 18 MINERAL 40 GR</b>			GREAT RESISTANCE (GR) POLYESTER
		REINFORCED BITUMEN SHEETS FOR WATERPROOFING - ELASTOPLASTOMERIC PROFESSIONAL MEMBRANE - APP COMPOUND			
PROPERTIES		Test Method	Unit	Tolerances	VALUE
LENGTH		EN 1848 -1	m	± 0,5%	<b>10</b>
WIDTH		EN 1848 -1	m	± 1%	<b>1</b>
THICKNESS		EN 1849 -1	mm	± 5%	<b>-</b>
MASS PER UNIT AREA		EN 1849 -1	Kg/m <sup>2</sup>	± 10%	<b>4</b>
TENSILE PROPERTIES:MAXIMUM TENSILE FORCE	L	EN 12311-1	N/50 mm	±20%	<b>650</b>
	T	EN 12311-1	N/50 mm	±20%	<b>500</b>
TENSILE PROPERTIES:ELONGATION	L	EN 12311-1	%	±15 abs.	<b>40</b>
	T	EN 12311-1	%	±15 abs.	<b>40</b>
RESISTANCE TO TEARING	L	EN 12310-1	N	±30%	<b>150</b>
	T	EN 12310-1	N	±30%	<b>150</b>
SHEAR RESISTANCE OF JOINTS	L	EN 12317-1	N/50 mm	>=	<b>550</b>
	T	EN 12317-1	N/50 mm	>=	<b>400</b>
PEEL RESISTANCE OF JOINTS		EN 12316-1	N/50 mm	>=	<b>NPD</b>
RESISTANCE TO IMPACT		EN 12691	mm	>=	<b>900</b>
RESISTANCE TO STATIC LOADING		EN 12730-1	Kg	>=	<b>15</b>
DIMENSIONAL STABILITY	L	EN 1107-1	%	<=	<b>±0,3%</b>
	T	EN 1107-1	%	<=	<b>±0,3%</b>
FLEXIBILITY AT LOW TEMPERATURE		EN 1109	°C	<=	<b>-15</b>
FLEXIBILITY AT LOW TEMP. AFTER ARTIFICIAL AGEING		EN 1296 - EN 1109	°C	<=	<b>NPD</b>
FLOW RESISTANCE AT ELEVATED TEMPERATURE		EN 1110	°C	>=	<b>130</b>
FLOW RESISTANCE AT ELEVATED TEM. AFTER ARTIFICIAL AGEING		EN 1296 - EN 1110	°C	>=	<b>120</b>
RESISTANCE TO ROOT PENETRATION		EN 13948	Statement	Pass	<b>NPD</b>
EXTERNAL FIRE PERFORMANCE		EN 13501-5	Class	Pass	<b>F roof</b>
REACTION TO FIRE		EN 13501-1	Class	Pass	<b>F</b>
WATERTIGHTNESS		EN 1928:2000 MET A	kPa	>=	<b>60</b>
ARTIFICIAL AGING BY COMBINATION OF UV RADIATION AND WATER		EN 1297	Statement	Pass	<b>NPD</b>
WATERTIGHTNESS AFTER ARTIFICIAL AGEING		EN 1296 - EN 1928	kPa	>=	<b>NPD</b>
WATERTIGHTNESS AFTER EXP. AGAINST CHEMICALS		EN 1847 - EN 1928	kPa	>=	<b>NPD</b>
FINISHING	SLATE FLAKES		POLYETHYLENE FILM		

NPD = No Performance Determined; L = Longitudinale Direction; T = Transversal Direction. Water vapour permeability factor  $\mu = 20.000$ . Thermal conductivity = 0,2 W/mK

For a correct use of the product refers to the technical documentation of the supplier. All tolerances as per EN 13707, EN 13969, EN 14695, EN 13859-1, EN 13970 and LINEE GUIDA AISPEC-MBP. This datasheet contains information that can be potentially changed without notice by BRAI. The technical data and the intended uses are in accordance with the regulations in force at the time of its issuance. BRAI provides the normal product guarantee with respect to the peculiar characteristic of waterproofing.

The product does not contain asbestos, asphalt within the meaning of D.LGS(Legislative Decree) N° 285/98

Brai s.r.l. - Zona Industriale Vascigliano I - 05039 - Stroncone - Terni/Italy  
Tel: +39/0744 1906412 Fax: +39/ 0744 1902054 E-mail: serviziotecnico@brai.it

REV 11/2016